

Novelis Pre-painted Aluminium	21.03.12
•	Page 1/7
ff3 – Pre-Painted Aluminium for Facades	Issue 1

This product description is valid for coil coated aluminium sheets and coils for the production frontage cladding systems.

The material is coated on both sides:

On top side with PVdF and on the bottom side with a protective lacquer. In addition the top side is covered by a strippable protective film

1. Processing Advises

The coils and sheets can be processed by cutting, blanking, punching and milling and be formed by bending. To avoid cracking during forming one has to adhere to a minimum inner bending radius and a minimum temperature.

- minimum inner bending radius:

2.5T according to DIN EN 13523-7 sheet gauge 3,0 mm: $R_i = 2.5 \times 3,0 \text{ mm} = 7,5 \text{ mm}$

To achieve a smaller bending radius the sheet may be grooved on the verse side in form of a broad rectangular groove and afterwards bent with a bending machine or press brake. For further details please refer to the Novelis ff2®, ff2plus® and ff3® "Construction Examples – Planning and Application".

- minimum metal temperature during forming process:

20 °C

2. Installation Advises

To ensure colour and gloss uniformity only sheets from productions with the same identification number are to be laid on one level of the facade. Sheets with metallic coatings must always be laid in the same direction. This also is proposed for solid colours.



Novelis Pre-painted Aluminium	21.03.12
	Page 2/7
ff3 – Pre-Painted Aluminium for Facades	Issue 1

An identification number is printed on the back side of the sheet. An arrow within the identification number indicates the coating direction.


No peel of paint during punching, drilling, bending process. Façade elements from ff3-sheet are statically determinable structural components. The stability against stresses can be calculated in all cases.

3. Metal Substrate

3.1 Alloy:	WG-53S acc. to Noveli EN AW-5754 [AIMg3] a with tighter tolerances AA 5754 acc. to interna	acc. to EN 573-3
3.2 Temper:	H42 acc. to Novelis de EN 1396 (WG-53S)	signation, with reference to
3.3 Mechanical Proper	ties (transverse to rollin according to internal st	ng direction): andard, EN 1396 and EN 10002-1
	$\begin{array}{l} \mbox{Tensile strength } R_m: \\ \mbox{Proof stress } R_{P0,2} & : \\ \mbox{Elongation } A_{50} & : \end{array}$	165 - 215 MPa

4. Dimensions and Tolerances according to EN 485-4 (DIN 1783) ½ EN

3,0 mm (including paint)	
< 1000 mm	+/- 0,06 mm
1001 - 1250 mm	+/- 0,08 mm
1251 – 1600 mm	+/- 0,09 mm
	< 1000 mm 1001 - 1250 mm



	re-painted Aluminium Painted Aluminium for Facades	6	21.03.12 Page 3/7 Issue 1
4.2 Widths:	501 - 1250 mm > 1250 mm	+ 1,7 / - 0 + 2,0 / - 0	
4.3 Lengths:5. Coatings	750 - 1000 mm 1001 - 3000 mm > 3000 mm	+ 3,0 / - 0 + 4,0 / - 0 + 5,0 / - 0) mm
5.1.1 Pre-treatment:	degreasing and chemical pre-tre according to internal standard.	eatment or	n both sides
5.1.2 Front:	PVdF (Polyvinylidenfluorid), Kynar 500 / Hylar 5000, 80/20 (80%PVdF, 20%Acrylic re	esin)	
2-coat-systems:	21-24 μm* tolerance (+2/-1 μ *depending on colour	m)	
gloss deviation hardness impact test adhesion cupping T-bend MEK-test surface UV-resist. ASS-test Water immersior	approx. 20-30 units, (acc. to DII depending on colour delta E <2 units (acc. to DIN EN F-H (acc. to DIN EN 13523-4) 40 ip/mm (acc. to DIN EN 1352 very good (acc. to DIN EN 1352 no de-lamination till fracture 2,5T (acc. to DIN EN 13523-7) >100 double rubs (acc. to DIN E uniform (internal standard) very good (internal standard) after 500 hrs of exposure no co corrosion creep from scratch les	I 13523-3) 3-5) 23-6) EN 13523- Trosion; ss than 2,0	11) mm
5.1.3 colours	according to Novelis colour char	t or on spe	ecial request.




Novelis Pre-painted Aluminium ff3 – Pre-Painted Aluminium for Facades		21.03.12 Page 4/7 Issue 1
5.1.4 reverse:	epoxy coat, transparent, Type 2916-25 thickness: approx. 3-4 μm	5
6. Coating Properties		
6.1 Front:	best colour and gloss durability, best resistance against corrosion and no chalking	chemical,
6.2 Back:	suitable for bonding with most of the av (2K-EP or 2K-PUR)	vailable glues
7. Protective Film	rotective Film To protect the material against damages during processing and installation the sheets are covered by white, UV-resistant protective film, which is printed wit Novelis symbol. This protective film can be easily strip off.	
	Thickness: 80 µm	
	The protective film must be removed la installation.	atest 6 months after

8. Quality Control

8.1 Test Procedures

Novelis Deutschland GmbH is certified according to DIN EN ISO 9001:2000 (Certificate Registration No: 08 100 939026, valid until 2010-10-21)



Novelis Pre-painted Aluminium	21.03.12
ff3 – Pre-Painted Aluminium for Facades	Page 5/7 Issue 1

The quality control is carried out in accordance with European guidelines such as EN, ISO, DIN and ECCA.

The following criteria are tested to the corresponding standard:

Tests

Standard

Metal SubstrateChemical compositionEN 573-3 (DIN 1725)Temper designationsEN 515Mechanical propertiesInternal standard, EN 1396Tensile testingEN 10002-1Tolerances on shape and DimensionsEN 485-4 (DIN 1783)

Coating properties

Pre-treatment Primer and top coat (thickness) Gloss Colour difference Lacquer hardness - Pencil Test Impact test Lacquer adhesion after cupping T-bend-test Lacquer hardening - MEK test Bonding test Surface quality

Accelerated Exposure Tests

Acetic acid salt spray test

EN 1396 Internal standard DIN EN 13523-1 DIN EN 13523-2 DIN EN 13523-3 DIN EN 13523-4 DIN EN 13523-5 DIN EN 13523-6 DIN EN 13523-7 DIN EN 13523-11 / Internal standard Internal standard Internal standard

DIN EN 13523-8 / ESS DIN 50021 / DIN EN ISO 9227 AASS under creep, blisters <1mm after 500h acc. to DIN EN 1396 table C.4 (see corrosion resistance index 3)



Novelis Pre-painted Al ff3 – Pre-Painted Alum	21.03.12 Page 6/7 Issue 1	
Water immersion resistance test QUV-Test	DIN EN 13523-9 not affected after 1000h DIN EN 13523-10 colour change < 5 Units	
Outdoor Exposure Tests at: Göttingen Hoek van Holland	Internal standard DIN EN 13523-19/21 / I	nternal Standard

9. Cleaning Easy to clean with clear water or pH-neutral detergents Graffiti can be easily removed from colours with gloss of 60 and 80. For all other colours environmentally friendly detergents are available in the market

Internal standard

10. Fire Protection Non-combustible A1, acc. to EN 13501

11. Health and safety aspects

Novelis Deutschland GmbH is certified according to:

- DIN EN ISO 14001 Environnemental Management
- OHSAS 18001:1999 Occupational Health and Safety Management
- The Novelis guide lines are laid down in the Novelis Code of Conduct
- Novelis issues yearly Environmental Declarations

12. Others

Florida

No toxic substances are released into the environment from paints used for these products.



Novelis Pre-painted Aluminium	21.03.12
ff3 – Pre-Painted Aluminium for Facades	Page 7/7 Issue 1

Any deviations to this product description are subject to a special agreement.

In the interest of technical progress we reserve the right to make any modifications.

We are not responsible for incorrect technical applications of our products.

Novelis Deutschland GmbH Werk Göttingen Hannoversche Str. 1 37075 Göttingen Germany

HBä / 12.02.2009